Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

: **CP-2020-12-30-78** **Date: 30/09/2020**

: Construction of Ward Office in Ward No.05, Byatarayanapura

: Sri.S K Keshavamurthy, #104, Sampigehalli, Jakkur Post, Bangalore-560064

: EE(Project)/Ynk Zone/WO/97/2020-21

: 25-09-20

: Footing Concrete

: 150X150X150 mm

: M25 / 7 Days Compressive Strength

: IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

: 30/09/2020

Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
Footing Concrete	M25	23/09/2020	30/09/2020	149.46 X 149.03 X 149.66	22274	**8.772**	519.9	23.3	22.5
Footing Concrete	M25	23/09/2020	30/09/2020	150.03 X 151.46 X 150.94	22723	**8.381**	503.7	22.2	
Footing Concrete	M25	23/09/2020	30/09/2020	150.51 X 150.08 X 150.53	22588	**8.828**	497.0	22.0	

Results obtained are satisfactory as per standard requirements.

Asst. Executive Engineer
Project Division
Yelahanka Zone
BBMP, Bangalore - 92

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL |
GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

: CP-2020-12-30-78 **Date: 21/10/2020**

: Construction of Ward Office in Ward No.05, Byatarayanapura

: Sri.S K Keshavamurthy, #104, Sampigehalli, Jakkur Post, Bangalore-560064

: EE(Project)/Ynk Zone/WO/97/2020-21

: 25-09-20

: Footing Concrete

: 150X150X150 mm

: M25 / 28 Days Compressive Strength

: IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

: 21/10/2020

Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
Footing Concrete	M25	23/09/2020	21/10/2020	151.48 X 151.96 X 149.97	23019	**8.810**	632.7	27.5	27.6
Footing Concrete	M25	23/09/2020	21/10/2020	151.09 X 151.61 X 151.16	22906	**8.575**	614.3	26.8	
Footing Concrete	M25	23/09/2020	21/10/2020	151.93 X 151.90 X 149.51	23077	**8.480**	658.5	28.5	

Remarks: Results are satisfactory as per standard requirements.

Asst. Executive Engineer
Project Division
Yelahanka Zone
BBMP, Bangalore - 92

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

M: 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL |
GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

: CP-2020-12-30-78 **Date: 30/09/2020**

: Construction of Ward Office in Ward No.05, Byatarayanapura

: Sri.S K Keshavamurthy, #104, Sampigehalli, Jakkur Post, Bangalore-560064

: EE(Project)/Ynk Zone/WO/97/2020-21

: 25-09-20

: Footing Concrete

: 150X150X150 mm

: M25 / 7 Days Compressive Strength

: IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

: 30/09/2020

Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
Footing Concrete	M25	23/09/2020	30/09/2020	150.78 X 150.10 X 149.05	22632	**8.772**	536.8	23.7	22.9
Footing Concrete	M25	23/09/2020	30/09/2020	151.78 X 151.04 X 149.61	22925	**8.381**	505.4	22.0	
Footing Concrete	M25	23/09/2020	30/09/2020	149.78 X 150.95 X 150.76	22610	**8.828**	519.2	23.0	

Remarks: Specimens received are satisfactory as per standard requirements.

Asst. Executive Engineer
Project Division
Yelahanka Zone
BBMP, Bangalore - 92

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL | GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

: CP-2020-12-30-78 **Date: 21/10/2020**

: Construction of Ward Office in Ward No.05, Byatarayanapura

: Sri.S K Keshavamurthy, #104, Sampigehalli, Jakkur Post, Bangalore-560064

: EE(Project)/Ynk Zone/WO/97/2020-21

: 25-09-20

: Footing Concrete

: 150X150X150 mm

: M25 / 28 Days Compressive Strength

: IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

: 21/10/2020

Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
	M25	23/09/2020	21/10/2020	149.30 X 151.05 X 149.90	22553	**8.810**	629.0	27.9	
	M25	23/09/2020	21/10/2020	150.06 X 149.10 X 150.88	22373	**8.575**	600.0	26.8	27.6
	M25	23/09/2020	21/10/2020	150.97 X 149.65 X 151.75	22592	**8.480**	632.6	28.0	

Remarks: Obtained are satisfactory as per standard requirements.

Asst. Executive Engineer
Project Division
Yelahanka Zone
BBMP, Bangalore - 92

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

Mob: 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL |
GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

: CP-2020-12-30-78 **Date: 12/10/2020**

: Construction of Ward Office in Ward No.05, Byatarayanapura

: Sri.S K Keshavamurthy, #104, Sampigehalli, Jakkur Post, Bangalore-560064

: EE(Project)/Ynk Zone/WO/97/2020-21

: 07-10-20

: Column Upto Plinth Beam Concrete

: 150X150X150 mm

: M25 / 7 Days Compressive Strength

: IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

: 12/10/2020

Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
Column Upto Plinth Beam Concrete	M25	05/10/2020	12/10/2020	151.19 X 149.83 X 150.89	22652	**8.772**	538.6	23.8	22.7
Column Upto Plinth Beam Concrete	M25	05/10/2020	12/10/2020	149.50 X 151.75 X 150.28	22686	**8.381**	503.5	22.2	
Column Upto Plinth Beam Concrete	M25	05/10/2020	12/10/2020	151.25 X 149.72 X 151.49	22646	**8.828**	502.9	22.2	

Remarks: Results obtained are satisfactory as per standard requirements.

Asst. Executive Engineer
Project Division
Yelahanka Zone
BBMP, Bangalore - 92

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

: CP-2020-12-30-78 **Date: 02/11/2020**

: Construction of Ward Office in Ward No.05, Byatarayanapura

: Sri.S K Keshavamurthy, #104, Sampigehalli, Jakkur Post, Bangalore-560064

: EE(Project)/Ynk Zone/WO/97/2020-21

: 07-10-20

: Column Upto Plinth Beam Concrete

: 150X150X150 mm

: M25 / 28 Days Compressive Strength

: IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

: 02/11/2020

Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
Column Upto Plinth Beam Concrete	M25	05/10/2020	02/11/2020	149.92 X 151.95 X 149.35	22781	**8.810**	619.0	27.2	27.2
Column Upto Plinth Beam Concrete	M25	05/10/2020	02/11/2020	149.90 X 151.34 X 150.56	22686	**8.575**	592.6	26.1	
Column Upto Plinth Beam Concrete	M25	05/10/2020	02/11/2020	150.66 X 149.76 X 151.42	22562	**8.480**	641.4	28.4	

The results obtained are satisfactory as per standard requirements.

Asst. Executive Engineer
Project Division
Yelahanka Zone
BBMP, Bangalore - 92

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL |
GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

: **CP-2020-12-30-78** **Date: 09/11/2020**

: Construction of Ward Office in Ward No.05, Byatarayanapura

: Sri.S K Keshavamurthy, #104, Sampigehalli, Jakkur Post, Bangalore-560064

: EE(Project)/Ynk Zone/WO/97/2020-21

: 04-11-20

: Plinth Beam Concrete

: 150X150X150 mm

: M25 / 7 Days Compressive Strength

: IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

: 09/11/2020

Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
	M25	02/11/2020	09/11/2020	150.70 X 151.24 X 149.06	22792	**8.772**	527.4	23.1	22.8
	M25	02/11/2020	09/11/2020	150.27 X 150.60 X 150.86	22631	**8.381**	520.2	23.0	
	M25	02/11/2020	09/11/2020	149.06 X 150.53 X 151.62	22438	**8.828**	498.0	22.2	

are satisfactory as per standard requirements.

Asst. Executive Engineer
Project Division
Yelahanka Zone
BBMP, Bangalore - 92

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

: CP-2020-12-30-78 **Date: 30/11/2020**

: Construction of Ward Office in Ward No.05, Byatarayanapura

: Sri.S K Keshavamurthy, #104, Sampigehalli, Jakkur Post, Bangalore-560064

: EE(Project)/Ynk Zone/WO/97/2020-21

: 04-11-20

: Plinth Beam Concrete

: 150X150X150 mm

: M25 / 28 Days Compressive Strength

: IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

: 30/11/2020

Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
M25	02/11/2020	30/11/2020	151.69 X 151.68 X 150.78	23008	**8.810**	643.7	28.0	27.6
M25	02/11/2020	30/11/2020	150.36 X 151.66 X 149.13	22804	**8.575**	606.9	26.6	
M25	02/11/2020	30/11/2020	150.40 X 151.86 X 149.49	22839	**8.480**	645.0	28.2	

satisfactory as per standard requirements.

Asst. Executive Engineer
Project Division
Yelahanka Zone
BBMP, Bangalore - 92

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

| Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL |
GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

: CP-2020-12-30-78 **Date: 09/11/2020**

: Construction of Ward Office in Ward No.05, Byatarayanapura

: Sri.S K Keshavamurthy, #104, Sampigehalli, Jakkur Post, Bangalore-560064

: EE(Project)/Ynk Zone/WO/97/2020-21

: 04-11-20

: Plinth Beam Concrete

: 150X150X150 mm

: M25 / 7 Days Compressive Strength

: IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

: 09/11/2020

Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
M25	02/11/2020	09/11/2020	150.33 X 150.26 X 150.42	22589	**8.772**	532.4	23.6	22.8
M25	02/11/2020	09/11/2020	151.63 X 151.45 X 150.48	22964	**8.381**	506.5	22.1	
M25	02/11/2020	09/11/2020	150.07 X 149.59 X 149.93	22449	**8.828**	510.0	22.7	

satisfactory as per standard requirements.

Asst. Executive Engineer
Project Division
Yelahanka Zone
BBMP, Bangalore - 92

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL |
GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

: CP-2020-12-30-78 **Date: 30/11/2020**

: Construction of Ward Office in Ward No.05, Byatarayanapura

: Sri.S K Keshavamurthy, #104, Sampigehalli, Jakkur Post, Bangalore-560064

: EE(Project)/Ynk Zone/WO/97/2020-21

: 04-11-20

: Plinth Beam Concrete

: 150X150X150 mm

: M25 / 28 Days Compressive Strength

: IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

: 30/11/2020

Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
M25	02/11/2020	30/11/2020	151.12 X 149.59 X 149.56	22607	**8.810**	612.0	27.1	27.3
M25	02/11/2020	30/11/2020	151.80 X 151.92 X 151.54	23061	**8.575**	599.8	26.0	
M25	02/11/2020	30/11/2020	149.83 X 151.80 X 151.44	22745	**8.480**	653.0	28.7	

satisfactory as per standard requirements.

Asst. Executive Engineer
Project Division
Yelahanka Zone
BBMP, Bangalore - 92

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

| Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL |
GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

: CP-2020-12-30-78 **Date: 03/11/2020**

: Construction of Ward Office in Ward No.05, Byatarayanapura

: Sri.S K Keshavamurthy, #104, Sampigehalli, Jakkur Post, Bangalore-560064

: EE(Project)/Ynk Zone/WO/97/2020-21

: 29-10-20

: Sump Bottom Slab Concrete

: 150X150X150 mm

: M25 / 7 Days Compressive Strength

: IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

: 03/11/2020

Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
M25	27/10/2020	03/11/2020	151.69 X 151.38 X 151.24	22963	**8.772**	538.4	23.4	22.8
M25	27/10/2020	03/11/2020	151.79 X 151.06 X 149.47	22929	**8.381**	504.5	22.0	
M25	27/10/2020	03/11/2020	149.46 X 149.00 X 151.94	22270	**8.828**	511.6	23.0	

satisfactory as per standard requirements.

Asst. Executive Engineer
Project Division
Yelahanka Zone
BBMP, Bangalore - 92

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL |
GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

: CP-2020-12-30-78 **Date: 24/11/2020**

: Construction of Ward Office in Ward No.05, Byatarayanapura

: Sri.S K Keshavamurthy, #104, Sampigehalli, Jakkur Post, Bangalore-560064

: EE(Project)/Ynk Zone/WO/97/2020-21

: 29-10-20

: Sump Bottom Slab Concrete

: 150X150X150 mm

: M25 / 28 Days Compressive Strength

: IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

: 24/11/2020

Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
	M25	27/10/2020	24/11/2020	151.74 X 150.84 X 150.69	22889	**8.810**	638.5	27.9	27.6
	M25	27/10/2020	24/11/2020	149.20 X 149.45 X 149.13	22298	**8.575**	601.4	27.0	
	M25	27/10/2020	24/11/2020	150.36 X 149.82 X 149.05	22526	**8.480**	630.8	28.0	

satisfactory as per standard requirements.

Asst. Executive Engineer
Project Division
Yelahanka Zone
BBMP, Bangalore - 92

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL |
GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

: **CP-2020-12-30-78** **Date: 05/11/2020**

: Construction of Ward Office in Ward No.05, Byatarayanapura

: Sri.S K Keshavamurthy, #104, Sampigehalli, Jakkur Post, Bangalore-560064

: EE(Project)/Ynk Zone/WO/97/2020-21

: 31-10-20

: Sump Side Wall Concrete

: 150X150X150 mm

: M25 / 7 Days Compressive Strength

: IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

: 05/11/2020

Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
Comp Side Wall Concrete	M25	29/10/2020	05/11/2020	150.35 X 151.62 X 151.47	22796	**8.772**	529.8	23.2	22.8
Comp Side Wall Concrete	M25	29/10/2020	05/11/2020	151.57 X 151.55 X 151.79	22970	**8.381**	524.7	22.8	
Comp Side Wall Concrete	M25	29/10/2020	05/11/2020	151.78 X 150.68 X 151.90	22870	**8.828**	511.3	22.4	

Remarks: Specimens received are satisfactory as per standard requirements.

Asst. Executive Engineer
Project Division
Yelahanka Zone
BBMP, Bangalore - 92

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

Mob: 9972914526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL |
GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

: **CP-2020-12-30-78** **Date: 26/11/2020**

: Construction of Ward Office in Ward No.05, Byatarayanapura

: Sri.S K Keshavamurthy, #104, Sampigehalli, Jakkur Post, Bangalore-560064

: EE(Project)/Ynk Zone/WO/97/2020-21

: 31-10-20

: Sump Side Wall Concrete

: 150X150X150 mm

: M25 / 28 Days Compressive Strength

: IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

: 26/11/2020

Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
M25	29/10/2020	26/11/2020	149.81 X 150.52 X 150.17	22548	**8.810**	623.1	27.6	27.4
M25	29/10/2020	26/11/2020	152.00 X 150.12 X 150.93	22817	**8.575**	601.1	26.3	
M25	29/10/2020	26/11/2020	151.05 X 149.74 X 149.41	22619	**8.480**	641.6	28.4	

satisfactory as per standard requirements.

Asst. Executive Engineer
Project Division
Yelahanka Zone
BBMP, Bangalore - 92

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

: CP-2020-12-30-78 **Date: 10/11/2020**

: Construction of Ward Office in Ward No.05, Byatarayanapura

: Sri.S K Keshavamurthy, #104, Sampigehalli, Jakkur Post, Bangalore-560064

: EE(Project)/Ynk Zone/WO/97/2020-21

: 05-11-20

: Sump Top Slab Concrete

: 150X150X150 mm

: M25 / 7 Days Compressive Strength

: IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

: 10/11/2020

	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
	M25	03/11/2020	10/11/2020	150.42 X 151.71 X 150.62	22819	**8.772**	543.7	23.8	22.9
	M25	03/11/2020	10/11/2020	151.31 X 149.51 X 151.89	22621	**8.381**	506.1	22.4	
	M25	03/11/2020	10/11/2020	150.46 X 150.66 X 150.85	22668	**8.828**	508.3	22.4	

satisfactory as per standard requirements.

Asst. Executive Engineer
Project Division
Yelahanka Zone
BBMP, Bangalore - 92

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

| Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL |
GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

: CP-2020-12-30-78 **Date: 01/12/2020**

: Construction of Ward Office in Ward No.05, Byatarayanapura

: Sri.S K Keshavamurthy, #104, Sampigehalli, Jakkur Post, Bangalore-560064

: EE(Project)/Ynk Zone/WO/97/2020-21

: 05-11-20

: Sump Top Slab Concrete

: 150X150X150 mm

: M25 / 28 Days Compressive Strength

: IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

: 01/12/2020

Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
M25	03/11/2020	01/12/2020	150.32 X 150.36 X 151.26	22601	**8.810**	616.1	27.3	27.4
M25	03/11/2020	01/12/2020	151.90 X 149.19 X 151.11	22662	**8.575**	607.5	26.8	
M25	03/11/2020	01/12/2020	149.79 X 149.10 X 150.36	22333	**8.480**	628.4	28.1	

satisfactory as per standard requirements.

Asst. Executive Engineer
Project Division
Yelahanka Zone
BBMP, Bangalore - 92

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

: CP-2020-12-30-78 **Date: 25/11/2020**

: Construction of Ward Office in Ward No.05, Byatarayanapura

: Sri.S K Keshavamurthy, #104, Sampigehalli, Jakkur Post, Bangalore-560064

: EE(Project)/Ynk Zone/WO/97/2020-21

: 20-11-20

: GF Column Concrete

: 150X150X150 mm

: M25 / 7 Days Compressive Strength

: IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

: 25/11/2020

Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
M25	18/11/2020	25/11/2020	151.70 X 149.10 X 149.12	22618	**8.772**	542.4	24.0	23.0
M25	18/11/2020	25/11/2020	149.15 X 150.37 X 149.17	22429	**8.381**	515.4	23.0	
M25	18/11/2020	25/11/2020	151.47 X 151.95 X 151.48	23017	**8.828**	507.5	22.0	

satisfactory as per standard requirements.

Asst. Executive Engineer
Project Division
Yelahanka Zone
BBMP, Bangalore - 92

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R.KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

: CP-2020-12-30-78 **Date: 16/12/2020**

: Construction of Ward Office in Ward No.05, Byatarayanapura

: Sri.S K Keshavamurthy, #104, Sampigehalli, Jakkur Post, Bangalore-560064

: EE(Project)/Ynk Zone/WO/97/2020-21

: 20-11-20

: GF Column Concrete

: 150X150X150 mm

: M25 / 28 Days Compressive Strength

: IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

: 16/12/2020

Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
M25	18/11/2020	16/12/2020	149.11 X 150.23 X 151.39	22400	**8.810**	605.2	27.0	27.5
M25	18/11/2020	16/12/2020	151.90 X 151.75 X 149.69	23050	**8.575**	621.9	27.0	
M25	18/11/2020	16/12/2020	151.37 X 151.81 X 149.60	22979	**8.480**	656.0	28.5	

satisfactory as per standard requirements.

Asst. Executive Engineer
Project Division
Yelahanka Zone
BBMP, Bangalore - 92

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

: CP-2020-12-30-78 **Date: 16/12/2020**

: Construction of Ward Office in Ward No.05, Byatarayanapura

: SriLS K Keshavamurthy, #104, Sampigehalli, Jakkur Post, Bangalore-560064

: EE(Project)/Ynk Zone/WO/97/2020-21

: 11-12-20

: GF Staircase Concrete

: 150X150X150 mm

: M25 / 7 Days Compressive Strength

: IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

: 16/12/2020

Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
M25	09/12/2020	16/12/2020	151.85 X 151.67 X 151.57	23030	**8.772**	538.8	23.4	22.9
M25	09/12/2020	16/12/2020	151.62 X 150.04 X 150.84	22749	**8.381**	515.8	22.7	
M25	09/12/2020	16/12/2020	149.38 X 150.32 X 150.36	22455	**8.828**	509.5	22.7	

satisfactory as per standard requirements.

Asst. Executive Engineer
Project Division
Yelahanka Zone
BBMP, Bangalore - 92

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

: CP-2020-12-30-78 **Date: 06/01/2021**

: Construction of Ward Office in Ward No.05, Byatarayanapura

: Sri.S K Keshavamurthy, #104, Sampigehalli, Jakkur Post, Bangalore-560064

: EE(Project)/Ynk Zone/WO/97/2020-21

: 11-12-20

: GF Staircase Concrete

: 150X150X150 mm

: M25 / 28 Days Compressive Strength

: IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

: 06/01/2021

Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
M25	09/12/2020	06/01/2021	151.07 X 151.38 X 150.42	22869	**8.810**	630.3	27.6	27.6
M25	09/12/2020	06/01/2021	151.29 X 149.54 X 151.83	22624	**8.575**	596.3	26.4	
M25	09/12/2020	06/01/2021	149.79 X 150.77 X 151.25	22583	**8.480**	652.8	28.9	

satisfactory as per standard requirements.

Asst. Executive Engineer
Project Division
Yelahanka Zone
BBMP, Bangalore - 92

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****